

Product properties		
<b>Format</b>	<b>Floor Fields</b>	
	2010 x 160 x 13 mm	<b>New Classics</b>
		1593 x 215 x 15 mm
<b>Top layer</b>	≥ 3.6 mm	
<b>Packaging</b>	Pack	9 Elements 2.894 m <sup>2</sup> / 19.395 kg
	Pallet	32 Packs 92.621 m <sup>2</sup> / 620.640 kg
		8 Elements 2.74 m <sup>2</sup> / 25.98 kg
		32 Packs 87.679 m <sup>2</sup> / 831.36 kg
<b>Warranty</b>	25 years	
<b>Notes</b>	- cleaning an maintenance see instructions - installation only by all-over adhesion - technical changes reserved	

### Product labelling



Quality  
Functionality  
Production  
Controlled  
  
www.tuv.com  
ID 1111211471

### Tolerances (EN 13489)

Admissible difference in length (± 0.1 %)	± 0.05 %
Admissible difference in width (± 0.2 mm)	± 0.1 mm
Squareness of the element (≤ 0.1 %)	≤ 0.05 %
Longitudinal curvature along the element (≤ 0.1 %)	≤ 0.05 %
Transverse curvature across the width (≤ 0.1 %)	≤ 0.08 %
Height differences of elements (≤ 0.2 mm)	≤ 0.18 mm
Moisture content at the time of first delivery (5-9%)	6 – 8 %

### Classification general product features

	Test method	Rating
Resistance to roller castor chairs	EN 425	We recommend the use of a conventional chairmat
Effect of a furniture leg	EN 424	No visible changes
<b>Thermal resistance</b> Suitable for installation over underfloor heating when using an appropriate underlay and moisture barrier.	EN 12664	Floor Fields: 0.087 m <sup>2</sup> *K/W New Classics: 0.1 m <sup>2</sup> *K/W
<b>E1</b> Formaldehyde (E1 = 0.1 ppm)	EN 717-1	≤ 0.05 ppm
Acoustical - Impact noise reduction	ISO 717-2	18 dB (with Akustik-Protect 100)
Disposal		Private waste disposal with normal household waste / bulky waste possible

### Classification surface characteristics

	Test method	Rating
Slip resistance	EN 13893	μ ≥ 0.47
	CEN/TS 15676	46 SRT (SRV wet)
		103 SRT (SRV dry)
Reaction to fire, click-installation as a floating floor	EN 13501-1	D <sub>fl</sub> s1
	Reaction to fire, installation by all-over adhesion	EN 13501-1
Chemical resistance	EN 13442	Category 4
Bond strength / Cross cutting test	ISO 2409	n.n.
Slip resistance, inclined plane	DIN 51130	R 10

Changed:	QMB	File name:	20170116_PA_TDS_Parkett_Edition_EN
Date:	01.08.2013	Update:	<a href="http://www.parador.eu/service/catalogues-downloads/technical-data-sheets">www.parador.eu/service/catalogues-downloads/technical-data-sheets</a>
Our technical data sheets are constantly updated and adapted to the latest technology. This version replaces all earlier versions and is valid from:			16.01.2017

Free sorting according to EN 13489		
Assortment:	Floor Fields	New Classics (french Herringbone pattern)
Characteristics according to EN 1310:	Upper side of the lamella	Upper side of the lamella
<b>Type of wood:</b>	<b>Oak</b>	
Botanical designation / Code (EN 13556):	Quercus petraea Liebl., Quercus robur L. / QCXE	
Origin:	DE, AT, HU, HR, SK, BA, UA, FR, CZ	
Shortcut / sorting / date (internal):	ES-LH-TT4-EI	ER-L-FGF-EI
	Version 12 2016	Version 1 2013
	N2	N2
<b>Sorting:</b>	<b>Select</b>	<b>Select</b>
Sound sapwood	not permitted	not permitted
Knot (intergrown)	permitted: up to 15 mm	not permitted
Falling out knot	not permitted	not permitted
Pinkknots	permitted	permitted: up to 5 mm
Filling	permitted	permitted
Slight crack/ haircrack	not permitted	not permitted
Sugar inclusions, mineral inclusions	-	-
Bark pocket	not permitted	not permitted
Lightning cracks	permitted: in knots	not permitted
Slope of grain	no criterion	no criterion
Healthy heart	not permitted	-
Medullary ray	permitted	permitted
Discoloration, colour variation	permitted: slight colour variations	permitted: slight colour variations
White streaks	-	-
Pilling sticks marking	not permitted	not permitted
Biodeterioration (EN 1311)	not permitted	not permitted
<b>Non-visible parts</b>		
All features without restrictions to size or quantity permitted, provided they do not affect the strength or durability of the floor.		
<b>Comment</b>		
Maximum 3% of lamellas are allowed in the next lower grading. Wood is a natural product and therefore different in colour and texture. Samples, brochures and photos are therefore only approximate and not binding. The action of sunlight affects the natural variation in wood shade. This allows the product present at the time of delivery of significant differences to master.		

Changed:	QMB	File name:	20170116_PA_TDS_Parkett_Edition_Anhang_EN
Date:	01.08.2013	Update:	<a href="http://www.parador.eu/service/catalogues-downloads/technical-data-sheets">www.parador.eu/service/catalogues-downloads/technical-data-sheets</a>
Our technical data sheets are constantly updated and adapted to the latest technology. This version replaces all earlier versions and is valid from:		16.01.2017	Page 1 of 1